| Approved ASSIFICATION & | 25X1 |
|---|---|
| - 2 | INTELLIGENCE AGENCY 25X1 |
| INFORM | ATION REPORT |
| COUNTRY USSR 25X1 | DATE DISTR. 29 Jun 51 |
| SUBJECT Technical Examination of S | Soviet Nylon Stocking: NO. OF PAGES 2 |
| PLACE ACQUIRED | 25X1 NO. OF ENCLS. |
| DATE ACQUIRED | SUPPLEMENT TO REPORT NO. |
| | 25X1 REPORT NO. |
| DATE OF INFORMATION | 23/(1 |
| THIS DOCUMENT CONTAINS INFORMATION AFFECTING THE NATIONAL DEFENSE OF THE UNITED STATES WITHIN THE MEANING OF THE ESPIONAGE ACT SO U.S. C., 31 AND 32. AS AMENDED. ITS TRANSMISSION OR THE REVELATION OF ITS CONTENTS IN ANY MANNER TO AN UNAUTHORIZED PERSON IS PRO- NIBITED BY LAW. REPRODUCTION OF THIS FORM IS PROMIBITED. | |
| | |
| 25X1 1. The stocking examined is desc | ribed as follows: |
| a. Visual examination id woman's stocking. | dentifies the item as a knitted, "full-fashioned" |
| Nylon No. 6 is identi several European prod | and the following of the many first and the first and the second of the |
| A small proportion of as titanium dioxide w | a crystalline substance tentatively identified as revealed by X-ray photographs. |
| 2. Microscopic and optical exami | nations of the sample have revealed the following: |
| a. The cross section of | the nylon filament is round and fattened round. |
| apparently with titan found. These cracks | of the filament shows that it is pigmented, dum dioxide. A few longitudinal cracks were were reported as caused by the pigment which has lines parallel to the axis of the fiber. |
| fraction; the differe index for light passi birefringence. This orientated (having it in one direction. The | congly birefringent having two indices of re- ence between the greatest and least refractive ing through the material being a measure of its reproperty indicates that the filament is highly is molecules ordered so that the majority point the observed orientation is attributed to the effect ents after they had been extruded. |
| 3. Physical properties of the ny | lon yarn were determined by tests to be as follows: |
| a. The denier is 52. Ni | ne thousand meters of the yarn weigh 52 grams. |
| b. The yarn consists of | 12 filaments. |
| c. The twist of the yarn | is 5.5 turns per inch. |
| | |
| | SECRET 25X1 |
| All the second of the second | |

| | | | CLA | SSIFICATIO | Ν | and the control of the control of | in the second | at . | en de marco de la compansión de la compa |
|-------|---|------|----------|------------|---|-----------------------------------|---------------|------|--|
| STATE | X | NAVY | X | NSRB | | DISTRIBUTION | | | |
| ARMY | X | AIR | $\bot X$ | FB! | M | I/ORR EV | | | I . |
| | | | | | | | | | |

- The make-up of the stocking is evaluated as follows:
 - the welt from hooks to needles of the knitting machine, so that the transfer could be accomplished with cotton loops.
 - The welt is too narrow and the number of fashioning courses is considerably less than is required to make a stocking of good shape, so that the upper leg is narrow while the ankle is wide.
 - The heel tabs have been linked instead of having been run on the needles of the knitting machine.
- Conclusions drawn from these observations are as follows:

25X1

25X1

Tenacity and elongation values for the yarn are within the range for comparable USA nylon yarns.

The denier is coarser than is usual in USA practice which would call for a yarn of not over 30 denier.

- Possibly the use of 52 denier yarn may indicate some lack of skill in yarn manufacture, processing, and knitting, since coarser yarns are easier to handle.
- (2) Alternatively, 52 denier yarn may have been chosen to produce a very durable service-weight stocking less subject to "runs."
- Use of cotton starting courses indicate that apparently the maker has difficulty in transferring the welt when using nylon.
- d. If a li inch needle is assumed, it is deduced that a 45 gauge knitting machine was used to make the stocking.

- end -

| 25X1 | | | | | | |
|------|--|--|--|--|--|--|
| | | | | | | |
| | | | | | | |
| | | | | | | |